

REPORT NO.: EFSN14040322C-C

DATE: MAY 19, 2014

PAGE: 1 of 3

## **TEST REPORT**

: CSP INC **APPLICANT** 

8248 W. ORANGE DR GLENDALE, AZ 85303 USA **ADDRESS** 

**SAMPLE DESCRIPTION** METAL RING WITH IMPRINT - BRO SIS BFF ETC

STYLE / ITEM NO. : K16-401

: KIDS' KORNER **BUYER** 

AGE REQUESTED ON APPLICATION FORM

: APR. 08, 2014; MAY 14, 2014 SAMPLE RECEIVED DATE

: APR. 09, 2014 TO MAY 16, 2014 **TEST PERIOD** 

**RESULT SUMMARY** 

TEST REQUESTED	RESULT
<ul> <li>Total Lead Content according to US Consumer Product Safety Improvement Act 2008 (CPSIA).</li> </ul>	PASS

SIGNED FOR AND ON BEHALF OF EUROFINS TESTING TECHNOLOGY (SHENZHEN) CO. LTD.

Inorganic Team Supervisor

Coco Luo

Organic Team Supervisor

This test report is valid for the tested samples only. Without permission

This test report does not entitle to carry his test report is not permitted to be duplicated in extracts.



REPORT NO.: EFSN14040322C-C

DATE: MAY 19, 2014

PAGE: 2 of 3

## **Material list**

Testing material No.	Component	Material	Colour
1	Coating on ring	Coating	Black
2	Coating on ring	Coating	Purple
3	Coating on ring	Coating	Blue
4	Substrate of ring	Metal	Silvery

## **Total Lead Content**

Test method : CPSC-CH-E1001-08.3; CPSC-CH-E1003-09.1

The sample was digested with acid. Then the lead content was determined by Inductively Coupled Plasma Optical Emission Spectrometry (ICP-OES).

Limit For surface coating materials: 90 ppm

For non-surface coating (substrate): 100 ppm

- according to US Consumer Product Safety Improvement Act 2008 (CPSIA

Sec.101).

Detection limit : 10 ppm

Test No.	Material No.	Test result (ppm)
Pb-1	1	N.D.
Pb-2	2	N.D.
Pb-3	3	N.D.
Pb-4	4	56

Note: -1 mg/kg = 1 ppm = 0.0001%

- N.D. = Not Detected

## Other Information / Remark:


N/A



REPORT NO.: EFSN14040322C-C

DATE: MAY 19, 2014

PAGE: 3 of 3



\*\*\*END OF THE REPORT\*\*\*