

# TEST REPORT

**APPLICANT** : CSP INC  
**ADDRESS** : 8248 W. ORANGE DR GLENDALE, AZ 85303 USA  
**SAMPLE DESCRIPTION** : SPORTS CAR PEN  
**STYLE / ITEM NO.** : K4-515  
**BUYER** : KIDS' KORNER  
**AGE REQUESTED ON APPLICATION FORM** : 3+  
**SAMPLE RECEIVED DATE** : APR. 28, 2015  
**TEST PERIOD** : APR. 28, 2015 TO APR. 30, 2015  
**RESULT SUMMARY** :

| TEST REQUESTED   | RESULT |
|--|--------|
| - Total Lead Content according to US Consumer Product Safety Improvement Act 2008 (CPSIA). | PASS   |

\*\*\*\*\*FOR FURTHER DETAILS, PLEASE REFER TO THE FOLLOWING PAGE(S)\*\*\*\*\*

SIGNED FOR AND ON BEHALF OF  
EUROFINS TESTING TECHNOLOGY (SHENZHEN) CO. LTD.



Harry Chen  
Assistant Lab Manager



Coco Luo  
Assistant Lab Manager



This test report is valid for the tested samples only. Without permission of the test center this test report is not permitted to be duplicated in extracts. This test report does not entitle to carry any safety mark on this or similar products.

**Material list**

| Testing material No. | Component                     | Material | Colour    |
|----------------------|-------------------------------|----------|-----------|
| 1                    | Pen                           | Plastic  | Blue      |
| 2                    | Pen                           | Plastic  | Dark blue |
| 3                    | Pen                           | Plastic  | Black     |
| 4                    | Pen                           | Plastic  | Yellow    |
| 5                    | Pen                           | Plastic  | Orange    |
| 6                    | Coating on wheels             | Coating  | Silvery   |
| 7                    | Substrate of wheels           | Plastic  | White     |
| 8                    | Tyre                          | Plastic  | Black     |
| 9                    | Axle of wheels                | Metal    | Silvery   |
| 10                   | Spring inside of pen          | Metal    | Silvery   |
| 11                   | Penpoint of refill            | Metal    | Silvery   |
| 12                   | Metal bead inside of Penpoint | Metal    | Silvery   |
| 13                   | Refill                        | Plastic  | White     |
| 14                   | Ink                           | Ink      | Blue      |

\*\*\*TO BE CONTINUED\*\*\*

**Eurofins Testing Technology (Shenzhen) Co. Ltd.**

4/F, Building# 3, Runheng Dingfeng Industrial Park, No.1 Liuxian 3rd Road, Bao'an District, Shenzhen, P.R. China  
 Tel.: +86 755 8358 5700 • Fax: +86 755 8358 5701 • Email: info.hk@eurofins.com • Website: [www.eurofins.com](http://www.eurofins.com) / [www.pt.eurofins.com](http://www.pt.eurofins.com)

**Total Lead Content**

Test method : CPSC-CH-E1001-08.3; CPSC-CH-E1002-08.3; CPSC-CH-E1003-09.1  
 The sample was digested with acid. Then the lead content was determined by Inductively Coupled Plasma Optical Emission Spectrometry (ICP-OES).

Limit : For surface coating materials: 90 ppm  
 For non-surface coating (substrate): 100 ppm  
 - according to US Consumer Product Safety Improvement Act 2008 (CPSIA Sec.101).

Detection limit : 10 ppm

| Test No. | Material No. | Test result (ppm) |
|----------|--------------|-------------------|
| Pb-1     | 6            | N.D.              |
| Pb-2     | 1            | N.D.              |
| Pb-3     | 2            | N.D.              |
| Pb-4     | 3            | N.D.              |
| Pb-5     | 4            | N.D.              |
| Pb-6     | 5            | N.D.              |
| Pb-7     | 7            | N.D.              |
| Pb-8     | 8            | N.D.              |
| Pb-9     | 9            | N.D.              |
| Pb-10    | 10           | N.D.              |
| Pb-11    | 11           | 60                |
| Pb-12    | 12           | N.D.              |
| Pb-13    | 13           | N.D.              |
| Pb-14    | 14           | N.D.              |

Note: - 1 mg/kg = 1 ppm = 0.0001%  
 - N.D. = Not Detected

**Other Information / Remark:**

N/A

\*\*\*TO BE CONTINUED\*\*\*

**Eurofins Testing Technology (Shenzhen) Co. Ltd.**

4/F, Building# 3, Runheng Dingfeng Industrial Park, No.1 Liuxian 3rd Road, Bao'an District, Shenzhen, P.R. China  
 Tel.: +86 755 8358 5700 • Fax: +86 755 8358 5701 • Email: info.hk@eurofins.com • Website: [www.eurofins.com](http://www.eurofins.com) / [www.pt.eurofins.com](http://www.pt.eurofins.com)

**Photo Attachment**  
**SPORTS CAR PEN****\*\*\*END OF THE REPORT\*\*\***