

TEST REPORT

APPLICANT : CSP INC
ADDRESS : 8248 W. ORANGE DR GLENDALE, AZ 85303 USA
SAMPLE DESCRIPTION : LIGHTED FOOTBALL PEN
STYLE / ITEM NO. : K5-611
BUYER : KIDS' KORNER
AGE REQUESTED ON APPLICATION FORM : 3+
SAMPLE RECEIVED DATE : MAY 17, 2016
TEST PERIOD : MAY 17, 2016 TO MAY 23, 2016
RESULT SUMMARY :

TEST(S) REQUESTED BY APPLICANT:	RESULT
- Total Lead Content according to US Consumer Product Safety Improvement Act 2008 (CPSIA).	PASS
- Total Lead Content with reference to customer's requirement with regard to California Proposition 65.	PASS

*****FOR FURTHER DETAILS, PLEASE REFER TO THE FOLLOWING PAGE(S)*****

SIGNED FOR AND ON BEHALF OF
EUROFINS TESTING TECHNOLOGY (SHENZHEN) CO. LTD.



Harry Chen
Assistant Lab Manager



Coco Luo
Assistant Lab Manager



This test report is valid for the tested samples only. Without permission of the test center this test report is not permitted to be duplicated in extracts.
This test report does not entitle to carry any safety mark on this or similar products.

Material list

Testing material No.	Component	Material	Colour
1	Lid of pen	Plastic	Semi-transparent white
2	Body of pen	Plastic	Black
3	Body of pen	Plastic	Yellow
4	Body of pen	Plastic	Orange
5	Coating on ball decoration of pen	Coating	White
6	Ball decoration of pen(substrate)	Plastic	Brown
7	Ball decoration of pen(substrate)	Plastic	Yellow
8	Ball decoration of pen(substrate)	Plastic	Orange
9	Holder of ball decoration on pen	Plastic/coating	Black/silvery
10	Bead inside of Penpoint	Metal	Silvery
11	Penpoint	Metal	Silvery
12	Ink	Ink	Blue
13	Refill	Plastic	White

TO BE CONTINUED

Eurofins Testing Technology (Shenzhen) Co. Ltd.

4/F, Building# 3, Runheng Dingfeng Industrial Park, No.1 Liuxian 3rd Road, Bao'an District, Shenzhen, P.R. China
 Tel.: +86 755 8358 5700 • Fax: +86 755 8358 5701 • Email: info.hk@eurofins.com • Website: www.eurofins.com / www.pt.eurofins.com

Total Lead Content (CPSIA)

Test method : CPSC-CH-E1001-08.3; CPSC-CH-E1002-08.3; CPSC-CH-E1003-09.1
 The sample was digested with acid. Then the lead content was determined by Inductively Coupled Plasma Optical Emission Spectrometry (ICP-OES).

Limit : For surface coating materials: 90 mg/kg
 For non-surface coating (substrate): 100 mg/kg
 - according to US Consumer Product Safety Improvement Act 2008 (CPSIA Sec.101).

Detection limit : 10 ppm

Test No.	Material No.	Test result (mg/kg)
Pb-1	1	N.D.
Pb-2	2	N.D.
Pb-3	3	N.D.
Pb-4	4	N.D.
Pb-5	5	N.D.
Pb-6	6	N.D.
Pb-7	7	N.D.
Pb-8	8	N.D.
Pb-9	9	N.D.
Pb-10	10	N.D.
Pb-11	11	52
Pb-12	12	N.D.
Pb-13	13	N.D.

Note: - 1 mg/kg = 1 ppm = 0.0001%
 - N.D. = Not Detected

TO BE CONTINUED

Eurofins Testing Technology (Shenzhen) Co. Ltd.

4/F, Building# 3, Runheng Dingfeng Industrial Park, No.1 Liuxian 3rd Road, Bao'an District, Shenzhen, P.R. China
 Tel.: +86 755 8358 5700 • Fax: +86 755 8358 5701 • Email: info.hk@eurofins.com • Website: www.eurofins.com / www.pt.eurofins.com

Total Lead Content (California Proposition 65)

Test method : CPSC-CH-E1001-08.3; CPSC-CH-E1002-08.3; CPSC-CH-E1003-09.1
 The sample was digested with acid. Then the lead content was determined by Inductively Coupled Plasma Optical Emission Spectrometry (ICP-OES).

Limit For surface coating materials: 90 ppm
 For non-surface coating (substrate): 100 ppm
 - with reference to customer's requirement with regard to California Proposition 65.

Detection limit : 10 ppm

Test No.	Material No.	Test result (ppm)
Pb-1	1	N.D.
Pb-2	2	N.D.
Pb-3	3	N.D.
Pb-4	4	N.D.
Pb-5	5	N.D.
Pb-6	6	N.D.
Pb-7	7	N.D.
Pb-8	8	N.D.
Pb-9	9	N.D.
Pb-10	10	N.D.
Pb-11	11	52
Pb-12	12	N.D.
Pb-13	13	N.D.

Note: - 1 mg/kg = 1 ppm = 0.0001%
 - N.D. = Not Detected

Other Information / Remark:

-According to the customer's requirement, the appointed materials have been tested.

TO BE CONTINUED

Eurofins Testing Technology (Shenzhen) Co. Ltd.

4/F, Building# 3, Runheng Dingfeng Industrial Park, No.1 Liuxian 3rd Road, Bao'an District, Shenzhen, P.R. China
 Tel.: +86 755 8358 5700 • Fax: +86 755 8358 5701 • Email: info.hk@eurofins.com • Website: www.eurofins.com / www.pt.eurofins.com

Photo Attachment**LIGHTED FOOTBALL PEN*******END OF THE REPORT*****